

Interflon Paste HT1200 (aerosol)

High temperature, food grade assembly paste & safe replacement for copper paste

Product description

Interflon Paste HT1200 (aerosol) is a universal assembly paste based on non-toxic ceramic materials with extraordinary properties for use under extreme circumstances. The product prevents corrosion, has a low coefficient of friction and prevents fretting of materials during the manufacture, assembly and disassembly of all kinds of machinery and equipment. Interflon Paste HT1200 (aerosol) is metal free and therefore safe for humans and environment.

Interflon Paste HT1200 (aerosol) is listed by the NSF for the use in applications with incidental food contact (NSF-H1) with registration number [137221](#) and ISO 21469 certified.

Application

For use in all screw connections and assembling of metal parts of all kind of machinery and equipment. For assembling and fitting of brakes, exhaust systems and turbo chargers systems, pneumatic tools, pins, plugs and everything else with a screw connection that is exposed to high pressures and temperatures. Very suitable as an environmental friendly alternative to copper paste and for use in stainless steel screw connections.

Advantages

- Low friction at assembly and disassembly
- Reduced risk of damage at disassembly
- Applicable at temperatures from -20°C till maximum +1200°C
- Strong corrosion protection
- Strong adherence on the surface; (will not pushed away during assembly)
- Doesn't dry out or crust like copper or aluminum pastes
- Aerosol can be used in every position

Instructions for use

Shake before use. Clean the parts to be assembled well and allow to dry. Spray Interflon Paste HT1200 (aerosol) thinly onto parts. Allow the solvents to evaporate for a while before assembly.

Safety regulations

See safety data sheet.

Packaging

See our current article list.

Transport regulations

See safety data sheet.

Interflon Paste HT1200 (aerosol)

High temperature, food grade assembly paste & safe replacement for copper paste

Technical data

Property	Result	Method
Composition	Mixture of mineral oils, solids, bentonite thickener, solvent, additives and MicPol®. Propellant propane, butane and isobutane.	
Colour	White	
Odour	Noticeable	
Density @ 20°C	1,14 g/cm ³	
Dynamic viscosity @20°C	400 Pas	ASTM D2983
Highest application temperature*	1200°C	
Friction coefficient	0.12 (steel-steel) 0.08 (titanium-steel)	
Shelf life**	6 years	

* High temperature limit is valid after evaporation of solvent.

** Shelf life of the product when stored at room temperature in the original and unopened packaging.

Typical properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance are to be expected during normal manufacture. The information contained herein is subject to change without notice.

INTERFLON BV, P.O. Box 1070
NL-4700 BB Roosendaal, The Netherlands
Tel. + 31 (0) 165 55 39 11 / www.interflon.com

This information is based on our present state of knowledge and is intended to provide general notes on our products and their uses. It should not therefore be construed as guaranteeing specific properties of the products described or their suitability for a particular application. Any existing industrial property rights must be observed. The quality of our products is guaranteed under our General Conditions of Sale.

Interflon®/MicPol® is a registered trademark of Interflon BV.